TÜVRheinland®
Precisely Right.

Partial Discharge Test

on reverse side foils of PV modules
according to IEC 60664-1, IEC61730

12.09.2007

Company / Examined foil:

COVEME SPA

DyMat TE transparent 175

PVF	25 micron	outside
Adhesive	5 micron	
PET	175 micron	
Adhesive	5 micron	
EVA	100 micron	cell side

* The EVA is not part of the directly encapsulation of the PV cells

Number of measurements: 10

Remarks: None

Extinction voltage		Deviation from the mean value (%)
Min. value in (V)	1141	-1,7
Mean value in (V)	1161	
Max. value in (V)	1183	1,9

The mean value minus the experimental standard deviation will be used to calculate the max. permissible voltage.
Experimental standard deviation: 15 V

Calculation of the max. permissible operating voltage on the basis of the ascertain values
Basis: **IEC 60664-1**

Umax = Ue x 1,414 / 1,2 x 1,25

1,414 Calculation of the peak value
1,2 Safety factor (humidity, temperature, etc.)
1,25 Safety factor (double or reinforced insul.)

Maximum permissible system voltage	**1080 VDC**

Testzentrum Energietechnik — Regenerative Energien

TÜV Rheinland Immissionsschutz und Energiesysteme GmbH, Am Grauen Stein, D-51105 Köln, Germany

212 07 887

9/505 01.07 TÜV, TUEV and TUV are registered trademarks. Utilisation and application requires prior approval.