

TRANSFER RELEASE FILM - Flocking

Hazy film one side primered for water based adhesives.
Antistatic treatment on the back side.
Heat stabilized for improved dimensional stability.

PROPERTY	Unit	Method	Value 75 µ	VALUE 100 µ
Thickness variation	mic	by weight	72 - 78	95 - 105
Yeld	sqm/kg	internal	9.52	7.14
Tensile strength (md)	Kg/cm2	ASTM D 882	1600 - 2500	1600 - 2500
Tensile strength (td)	Kg/cm2	ASTM D 882	1700 - 2800	1700 - 2800
Elongation at break (md)	%	ASTM D 882	100 - 200	100 - 200
Elongation at break (td)	%	ASTM D 882	100 - 200	100 - 200
DYNE VALUE (treated side)	Dynes/cm	ASTM D 2758	>58	>58
Shrinkage (md) (150°C x 30 minutes)	%	ASTM D 1204	< 0,3	< 0,3
Shrinkage (td) (150°C x 30 minutes)	%	ASTM D 1204	< 0,3	< 0,3
SURFACE RESISTIVITY	Ohms/	ASTM D 257	< 10 ¹⁰	< 10 ¹⁰

The above information is given in good faith and is generally reliable. However, the customer will have to examine the suitability of the film for individual application. Hence no general or particular warranty for the applications of the film is offered by us. The above information is liable to change due to innovation and improvement in the manufacturing process. We assume no liability for any infringement of any patent, copyright or design on the part of the customer while exploiting the film for different end-uses.

Revision: february 2010