

PHOTOVOLTAIC

BACKSHEET FOR PV MODULE PROTECTION

Laminate based on two layers, Tedlar®//PET

Thanks to its excellent resistance to the atmospheric agents, its strong barrier to oxygen and humidity, the high voltage insulation and the long term resistance to the hydrolysis of adhesives, dyMat®cTE is properly indicated for solar cell module encapsulation.

The PET side is treated with a special thick primer wich provides extremely high bonding to EVA. Tedlar®** and primer can be supplied in different colours** and in transparent finishing. The laminate thickness has been designed to provide the best combination of properties in terms of electrical insulation and weatherability.

	Unit	Method	Typical values
PET thickness	micron	caliper	125
Tedlar® thickness	micron	caliper	25
Primer thickness	micron	caliper	100
Laminate thickness	micron	caliper	270 +/- 5%
Unit weight	gr/sqm	10x10 weight	327 +/- 5%
Tensile strength (MD)	N/10 mm	ASTM D-882	180
Tensile strength (TD)	N/10 mm	ASTM D-882	220
Elongation at break (MD)	%	ASTM D-882	140
Elongation at break (TD)	%	ASTM D-882	115
Heat shrinkage (MD) 150°C x 30'	%	ASTM D-1204	< 1,2
Heat shrinkage (TD) 150°C x 30'	%	ASTM D-1204	< 0,6
Layer peel strength	N/10 mm	T - peel (peak value)	> 5
EVA adhesion *** (primer coated side vs EVA)	N/10 mm	internal	> 40
Moisture barrier (at 38° 90% RH)	gr/sqm x day	ASTM F-1249	2,8
Breakdown voltage	kV	ASTM D-149	> 15
Partial discharge test	VDC	IEC 60664-1	> 1000

Legend

* Tedlar colours available on request

** Primer colours available: W (white), BK (black) and BL (blue). Other colours available upon request

***EVA Corona treated available upon request (adhesion typically > 80N/10mm)

Notes

Other thicknesses on request

Cut sheets (sizes, drills etc.) according to customer's specifications

Shelf life: 2 years

All values stated are to be considered as Typical values.

The above information is liable to change due to innovation and improvement in the manufacturing process.

We assume no liability for any infringement of any patent, copyright or design on the part of the customer while exploiting the film for different end-uses.

Date of revision: April 2010

dyMat® is TÜV certified and UL recognized



UL file n° E313506



dyMat® is a Coveme registered trade mark

Coveme spa is UNI EN ISO 9001-2008 certified

