

FILMS WITHOUT PRIMER

Transparent, heat stabilized polyester film for elevated dimensional stability.

PROPERTY	UNIT	METHOD	VALUE 23 μ	VALUE 50 μ	VALUE 75 μ	VALUE 100 μ	VALUE 125 μ	VALUE 175 μ
THICKNESS VARIATION	micron	internal	21,8 - 24,2	47,5 - 52,9	72,0 - 78,0	95,0 - 105,0	119,0 - 131,0	166,0 - 184,0
DENSITY	gm/cm3	ASTM D 1505	1,4	1,4	1,4	1,4	1,4	1,4
YELD	sqm/kg	internal	14,28	9,52	7,14	5,71	5,71	4,08
TENSILE STRENGTH (MD)	Kg/cm2	ASTM D 882	1800 - 3100	1750 - 2500	1500 - 2500	1600 - 2500	1600 - 2500	1700 - 3000
TENSILE STRENGTH (TD)	Kg/cm2	ASTM D 882	1800 - 2800	1900 - 2800	1800 - 2800	1700 - 2800	1700 - 2800	1700 - 3000
ELONGATION AT BREAK (MD)	%	ASTM D 882	90 - 180	90 - 180	90 - 180	90 - 180	90 - 180	90 - 180
ELONGATION AT BREAK (TD)	%	ASTM D 882	90 - 180	90 - 180	90 - 180	90 - 180	90 - 180	90 - 180
SHRINKAGE (MD) (150°C FOR 30MIN)	%	ASTM D 1204	AVERAGE 0,7	< 0,3	< 0,3	< 0,2	< 0,2	< 0,2
SHRINKAGE (TD) (150°C FOR 30MIN)	%	ASTM D 1204	< 0,2	< 0,2	< 0,2	< 0,2	< 0,2	< 0,2

The above information is given in good faith and is generally reliable. However, the customer will have to examine the suitability of the film for individual application. Hence no general or particular warranty for the applications of the film is offered by us. The above information is liable to change due to innovation and improvement in the manufacturing process. We assume no liability for any infringement of any patent, copyright or design on the part of the customer while exploiting the film for different end-uses.

