

**HIGH SURFACE TENSION FILMS**

White pet film one (HP) or two sides (HPH) treated for elevated bonding with conductive inks, adhesive masses and lacquers thanks to the high surface tension of the film.

PROPERTY	UNIT	METHOD	VALUE 50 µ	VALUE 75 µ	VALUE 100 µ	VALUE 125 µ	VALUE 175 µ	VALUE 250 µ	VALUE 330 µ
THICKNESS VARIATION	micron	internal	47,5 - 52,9	72,0 - 78,0	95,0 - 105,0	119,0 - 131,0	166,0 - 184,0	237,0 - 262,0	327,0 - 343,0
DENSITY	gr/m3	ASTM D 1505	1,41	1,41	1,41	1,41	1,41	1,41	1,41
YIELD	sqm/Kg	internal	14,08	9,39	7,14	5,71	4,08	2,82	2,13
TENSILE STRENGTH (MD)	Kg/cm2	ASTM D 882	> 1250	> 1250	> 1250	> 1250	> 1250	> 1250	> 1250
TENSILE STRENGTH (TD)	%	ASTM D 882	> 1550	> 1550	> 1550	> 1550	> 1550	> 1550	> 1550
ELONGATION AT BREAK (MD)	%	ASTM D 882	> 50	> 50	> 50	> 50	> 50	> 50	> 50
ELONGATION AT BREAK (TD)	sec BEKK	ASTM D 882	> 50	> 50	> 50	> 50	> 50	> 50	> 50
WETTING TENSION	Dynes/cm	ASTM D 2578	> 58	> 58	> 58	> 58	> 58	> 58	> 58
HEAT SHRINKAGE (MD) (150°C FOR 30 MIN)	%	ASTM D 1204	< 2,0	< 1,8	< 1,5	< 1,5	< 1,5	< 1,5	< 1,5
HEAT SHRINKAGE (TD) (150°C FOR 30 MIN)	%	ASTM D 1204	< 1,5	< 1,5	< 1,0	< 1,0	< 1,0	< 1,0	< 1,0
WHITENESS		ASTM D 313	> 90	> 90	> 90	> 90	> 90	> 90	> 90
TOTAL LIGHT TRANSMISSION	%	ASTM D 1003	< 23	< 18	< 10	< 8	< 5	< 4	< 2

The above information is given in good faith and is generally reliable. However, the customer will have to examine the suitability of the film for individual application. Hence no general or particular warranty for the applications of the film is offered by us. The above information is liable to change due to innovation and improvement in the manufacturing process. We assume no liability for any infringement of any patent, copyright or design on the part of the customer while exploiting the film for different end-uses.



Kemafoil® is a Coveme registered trademark

Coveme spa is UNI EN ISO 9001-2008 and ISO 14001 certified

Date of revision: July 2012