

FILMS FOR LASER PRINT

Coated and heat-stabilised white opaque film for B&W and colour laser printing.

PROPERTY	UNIT	METHOD	VALUE 50 µ	VALUE 75 µ	VALUE 100 µ	VALUE 125 µ	VALUE 175 µ	VALUE 250 µ
TOTAL WEIGHT	gr/m ²	internal	74 - 80	102 - 110	142 - 150	174 - 184	248 - 258	353 - 363
COATING WEIGHT	gr/m ²	internal	4 - 6	4 - 6	4 - 6	4 - 6	4 - 6	4 - 6
TENSILE STRENGTH (MD)	Kg/cm ²	ASTM D 882	> 1250	> 1250	> 1250	> 1250	> 1250	> 1250
TENSILE STRENGTH (TD)	Kg/cm ²	ASTM D 882	> 1550	> 1550	> 1550	> 1550	> 1550	> 1550
ELONGATION AT BREAK (MD)	%	ASTM D 882	> 50	> 50	> 50	> 50	> 50	> 50
ELONGATION AT BREAK (TD)	%	ASTM D 882	> 50	> 50	> 50	> 50	> 50	> 50
SMOOTHNESS	sec BEKK	SMOOTHME-TER	> 40	> 40	> 40	> 40	> 40	> 40
TOTAL LIGHT TRANSMISSION	%	ASTM D 1003	< 23	> 18	> 10	> 8	> 5	> 4
HEAT SHRINKAGE (MD) (150°C FOR 30 MIN)	%	ASTM D 1204	< 0,6	< 0,6	< 0,6	< 0,6	< 0,6	< 0,6
HEAT SHRINKAGE (TD) (150°C FOR 30 MIN)	%	ASTM D 1204	< 0,4	< 0,4	< 0,4	< 0,4	< 0,4	< 0,4

The above information is given in good faith and is generally reliable. However, the customer will have to examine the suitability of the film for individual application. Hence no general or particular warranty for the applications of the film is offered by us. The above information is liable to change due to innovation and improvement in the manufacturing process. We assume no liability for any infringement of any patent, copyright or design on the part of the customer while exploiting the film for different end-uses.

Kemafoil® is a Coveme registered trademark



Coveme spa is UNI EN ISO 9001-2008 and ISO 14001 certified

Date of revision: July 2012