

FILMS FOR INDOOR TAGS

White opaque petp film, double side coated for computer printing. Heat stabilized for laser printers and top coated for improved toner adhesion and antistatic properties.

PROPERTY	UNIT	METHOD	VALUE 50 μ	VALUE 75 μ	VALUE 100 μ	VALUE 125 μ	VALUE 175 μ	VALUE 250 μ
TOTAL WEIGHT	gr/m2	internal	76 - 84	113 - 122	148 - 190	180 - 190	250 - 260	355 - 365
COATING WEIGHT	gr/m2	internal	7 - 12	7 - 12	7 - 12	7 - 12	7 - 12	7 - 12
TENSILE STRENGTH (MD)	Kg/cm2	ASTM D 882	> 1250	> 1250	> 1250	> 1250	> 1250	> 1250
TENSILE STRENGTH (TD)	Kg/cm2	ASTM D 882	> 1550	> 1550	> 1550	> 1550	> 1550	> 1550
ELONGATION AT BREAK (MD)	%	ASTM D 882	> 50	> 50	> 50	> 50	> 50	> 50
ELONGATION AT BREAK (TD)	%	ASTM D 882	> 50	> 50	> 50	> 50	> 50	> 50
SMOOTHNESS	sec BEKK	SMOOTHMETER	> 40	> 40	> 40	> 40	> 40	> 40
TOTAL LIGHT TRANSMISSION	%	ASTM D 1003	< 23	< 18	< 10	< 8	< 5	< 4
SURFACE RESISTIVITY	%	ASTM D 257	< 1 X 10 ¹⁰	< 1 X 10 ¹⁰	< 1 X 10 ¹⁰	< 1 X 10 ¹⁰	< 1 X 10 ¹⁰	< 1 X 10 ¹⁰
HEAT SHRINKAGE (MD) (150°C FOR 30 MIN)	%	ASTM D 1204	< 0,8	< 0,8	< 0,8	< 0,8	< 0,8	< 0,8
HEAT SHRINKAGE (TD) (150°C FOR 30 MIN)	%	ASTM D 1204	< 0,5	< 0,5	< 0,5	< 0,5	< 0,5	< 0,5

The above information is given in good faith and is generally reliable. However, the customer will have to examine the suitability of the film for individual application. Hence no general or particular warranty for the applications of the film is offered by us. The above information is liable to change due to innovation and improvement in the manufacturing process. We assume no liability for any infringement of any patent, copyright or design on the part of the customer while exploiting the film for different end-uses.



Kemafoil® is a Coveme registered trademark

Coveme spa is UNI EN ISO 9001-2008 and ISO 14001 certified

Date of revision: July 2012