

FILM FOR OUTDOOR TAGS

Matt white polyester film, double side coated for computer printing. Heat stabilized for laser printers with improved water resistance.

PROPERTY	UNIT	METHOD	VALUE 125 μ	VALUE 175 μ
BASE FILM THICKNESS	micron	internal	118 - 132	167 - 184
TOTAL WEIGHT	gr/m2	internal	184 - 204	255 - 280
COATING WEIGHT	gr/m2	internal	11 - 16	11 - 16
TENSILE STRENGTH (MD)	Kg/cm2	ASTM D 882	> 1250	> 1250
TENSILE STRENGTH (TD)	Kg/cm2	ASTM D 882	> 1550	> 1150
ELONGATION AT BREAK (MD)	%	ASTM D 882	> 50	> 50
ELONGATION AT BREAK (TD)	%	ASTM D 882	> 50	> 50
SMOOTHNESS	sec BEKK	SMOOTHMETER	20 - 28	20 - 28
SURFACE RESISTIVITY	ohm/square	ASTM D 257	1.0E+08 - 1.0E + 10	1.0E+08 - 1.0E + 10
HEAT SHRINKAGE (MD) (150°C FOR 30 MIN)	%	ASTM D 1204	< 0,5	< 0,5
HEAT SHRINKAGE (TD) (150°C FOR 30 MIN)	%	ASTM D 1204	< 0,5	< 0,5

The above information is given in good faith and is generally reliable. However, the customer will have to examine the suitability of the film for individual application. Hence no general or particular warranty for the applications of the film is offered by us. The above information is liable to change due to innovation and improvement in the manufacturing process. We assume no liability for any infringement of any patent, copyright or design on the part of the customer while exploiting the film for different end-uses.

Kemafoil® is a Coveme registered trademark



Coveme spa is UNI EN ISO 9001-2008 and ISO 14001 certified

Date of revision: November 2012