

FLEXIBLE PACKAGING - Metallised Copolymer Based

COVEME Cop M/C (B) 12 μ is a biaxially oriented Polyethylene Terephthalate Film metallised on Copolyester Coated side, other side corona treated.

COVEME Cop M/C (B) 12 μ has been designed for converting, in triplex structure where good barrier properties and high bonding is required.

PROPERTY	TYPICAL VALUE	UNIT	METHOD
Thickness	11,7 - 12,3	μ	Internal Method
Density	1,395 - 1,405	g/cm ³	ASTM D 1505
Yield	59,5	m ² /Kg	Internal Method
Tensile strength (md)	1900 - 3000	kg/cm ²	ASTM D 882
Tensile strength (td)	1900 - 3100	kg/cm ²	ASTM D 882
Elongation at break (md)	90 - 170	%	ASTM D 882
Elongation at break (td)	90 - 160	%	ASTM D 882
Heat Shrinkage (md) (150°C 30 min.)	1,0 - 2,5	%	ASTM D 1204
Heat Shrinkage (td) (150°C 30 min.)	0,0 - 1,0	%	ASTM D 1204
C.o.f. static	< 0,6		ASTM D 1894
C.o.f. kinetic	< 0,55		ASTM D 1894
Wetting tension Aluminum Side	> 50	dynes/cm	ASTM D 2578
Wetting tension Corona Side	> 50	dynes/cm	ASTM D 2578
Optical Density (B)	1,8 - 2,1	%	ASTM D 103
O ₂ transmission Typical @ 23°C - 0% RH	1,0 - 1,2	cc/m ² x 24h x atm	ASTM D 3985
Water Vapor Tr Typical @ 38°C - 90% RH	1,3	g/m ² x 24h x atm	ASTM E 96

The metallised layer should be protected against humidity and scratching, the material and its technical specification are guaranteed for a period of 6 month from delivery.

The above information is given in good faith and is generally reliable. However, the customer will have to examine the suitability of the film for individual application. Hence no general or particular warranty for the applications of the film is offered by COVEME. The above information is liable to change due to innovation and improvement in the manufacturing process. COVEME assume no liability for any infringement of any patent, copyright or design on the part of the customer while exploiting the film for different end-uses.

Revision: July 2012

Coveme spa is UNI EN ISO 9001-2008 and ISO 14001 certified

