

TRANSFER RELEASE FILM - Silk Screen

Two side matt release film for transfer application with cold and hot peel off.
Heat stabilized for better dimensional stability.
Suitable for silk screen with water based PU inks.

PROPERTY	Unit	Method	Value 75 µ	VALUE 100 µ
Total Weight	gr/m2	internal	113 - 117	148 - 156
Coating Weight	gr/m2	internal	8-12	8-12
Tensile strength (md)	Kg/cm2	ASTM D 882	1500 - 2500	1600 - 2500
Tensile strength (td)	Kg/cm2	ASTM D 882	1800 - 2800	1700 - 2800
Elongation at break (md)	%	ASTM D 882	100 - 200	100 - 200
Elongation at break (td)	%	ASTM D 882	100 - 200	100 - 200
Opacity	%	Photovolt		Avg 27
Smoothness	sec Bekk	SMOOTHMETER		typical 40
Shrinkage (md) (150°C x 30 minutes)	%	ASTM D 1204	< 0,3	< 0,3
Shrinkage (td) (150°C x 30 minutes)	%	ASTM D 1204	< 0,3	< 0,3

All values stated are to be considered as Typical values.

The above information is liable to change due to innovation and improvement in the manufacturing process.

We assume no liability for any infringement of any patent, copyright or design on the part of the customer while exploiting the film for different end-uses.

Kemafoil® is a Coveme registered trademark



Coveme spa is UNI EN ISO 9001-2008 and ISO 14001 certified

Date of revision: July 2012