

TRANSFER RELEASE FILM - Digital

Two side matt release film for transfer application with cold peel off.
Heat stabilized for better dimensional stability.
Suitable for Digital printing with Indigo printing machines.
Silk screen process for thermoadhesive needed

PROPERTY		Unit	Method	VALUE 100 µ
Total Weight		gr/m2	internal	148-156
Tensile strength	MD	Kg/cm2	ASTM D 882	1600 - 2500
	TD	Kg/cm2	ASTM D 882	1700 - 2800
Elongation at break	MD	%	ASTM D 882	100 - 200
	TD	%	ASTM D 882	100 - 200
Shrinkage	MD	%	ASTM D 1204	< 0,3
Shrinkage (md) (150°C x 30 minutes)	TD	%	ASTM D 1204	< 0,3

All values stated to be considered as Typical values.

The above information is liable to change due to innovation and improvement in the manufacturing process.

We assume no liability for any infringement of any patent, copyright or design on the part of the customer while exploiting the film for different end-uses.

Kemafoil® is a Coveme registered trademark



Coveme spa is UNI EN ISO 9001-2008 and ISO 14001 certified Date of revision: September 2016